



PLYMAN

GREATER SELECTION • BETTER VALUE

PRODUCT DATA SHEET

Radiata Flooring Plywood

- **Description:** Natural rotary peeled, wood veneer plywood sheets.
- **Specie:** Radiata Pine
- **Size:** 2400 x 1200
- **Thickness,** 19mm 9 ply
- **Construction** 21mm 9 ply
- **Typical Weights:**
- **Colours:** Pale cream
- **Texture:** Even texture, fine grain surface with allowable defects. Plastic tongue and grooved edges.
- **Source:** NZ plantation grown Radiata Pine.
- **Grades:** CD : General appearance face sanded two sides for paint or non decorative finish f8 stress grade.
- **Glue Bond:** A Bond - Marine Phenolic formaldehyde resin, 72 hour boil test. Commonly known as WBP (weather and boil proof) or A bond.
- **Workability:** Quality economic product reflecting high utilization of renewable timber resource. Produces strong, medium weight, stable panels. Machines, glues and finishes well.
- **Preservation:** Untreated : natural, non durable.
CCA : can be specified for exterior H3 (green) application.
Not suitable for ground contact
- **Durability:** Non durable. Note that plywood is not required to be naturally durable. Thorough sealing with preservative compounds, paints or resins is necessary.
- **Uses:** CD : General purpose flooring construction plywood substrate for paint or non decorative locations
- **Storage:** Keep dry, store undercover, stack clear of ground, on bearers

NB. Rotary peeled veneering yields veneers of all grades. Plywood faces are selected to a high quality but this is a volume production method which allows some surface roughness with occasional splits and checks. Comparison of slice cut veneers may give a false expectation as slice-cut veneers provide a smoother, tighter surface.